

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets




(11) Publication number:

0 496 323 A2

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **92100847.0**(51) Int. Cl.⁵: **G02B 1/04, G02F 1/13,
G09F 9/00**(22) Date of filing: **20.01.92**(30) Priority: **22.01.91 JP 20328/91**
27.03.91 JP 63517/91(43) Date of publication of application:
29.07.92 Bulletin 92/31(84) Designated Contracting States:
BE DE FR GB IT LU NL(71) Applicant: **TORAY INDUSTRIES, INC.**
2-1, Nihonbashi Muromachi 2-chome
Chuo-ku
Tokyo 103(JP)(72) Inventor: **Miyakawa, Katsutoshi**
16, Takehana Jizoji, Minami-machi,
Yamashina-ku
Kyoto-shi, Kyoto 607(JP)
Inventor: **Tsunashima, Kenji**
1-22, Daigo Kamihayama-cho, Fushimi-ku
Kyoto-shi, Kyoto 601-13(JP)
Inventor: **Aoki, Seizo**
454, Oono, Tsuchiyama
Koka-gun, Shiga, 528-02(JP)(74) Representative: **Kador & Partner**
Corneliusstrasse 15
W-8000 München 5(DE)(54) **Reflector for a surface light source.**

(57) A reflector (11) used in a surface light source comprising a white polyester film in which fine voids are formed and whose apparent specific gravity is in the range of 0.5 to 1.2. The reflectance of the polyester film can be increased by the fine voids. When the reflector having a high reflectance is used in a surface light source having a side light system, a bright scope easy to see can be obtained.

FIG. 1

The present invention relates to a reflector used in a surface light source, and more particularly to a substrate used for a reflector of a surface light source, which can obtain a bright scope when a side light system (also called an edge light system) is employed for the surface light source as a method for illuminating a scope of a liquid crystal display or an electric decorative board etc.

A back light system, wherein a display is lighted from back surface side, has been employed as a method for illuminating a scope of a liquid crystal display or an electric decorative board. Recently, however, a side light system, such as a system disclosed in JP-A-SHO 63-62104, has been broadly applied therefor, from the viewpoints of advantages that the system can be constituted thin and that the scope can be uniformly illuminated. In the side light system, halftone dots are printed on one surface of a transparent substrate having a certain thickness such as an acrylic plate, and a light from a light source such as a cold cathode ray tube is applied to the substrate through the edge of the substrate. The applied light is uniformly dispersed by the halftone dot print, and a scope having a uniform brightness can be obtained. Further, since the light source is disposed at a position not in the back surface side but in the edge side, the side light system can be made thinner than a back light system.

FIG. 3 illustrates a typical side light system. A reflector 11 (reflecting plate) is provided on one surface of a transparent light guiding plate 14 comprising a transparent substrate, on which halftone dots 15 are printed. A diffusion plate 13 and a liquid crystal display 12 are disposed on the other surface side. A light emitted from a cold cathode ray tube 16 is introduced through the edge of transparent light guiding plate 14 into the interior thereof. The light is uniformly dispersed by halftone dots 15, and the light reflected by reflector 11 illuminates a scope of liquid crystal display 12 brightly.

In such a side light system, a reflector must be provided on the back surface side of a scope (the back surface side of a transparent light guiding plate) in order to prevent an introduced light from escaping to the back side. This reflector is required to be thin and to have a high reflectance property. Although a metal deposited layer such as one disclosed in JP-A-SHO 62-169105 or a white synthetic paper such as one disclosed in JP-A-SHO 63-62104 is tried to be used as the reflector, the deposited layer is expensive and the synthetic paper cannot achieve a sufficiently bright scope. Accordingly, in practice, a white polyester film in which a white pigment such as titanium oxide is added, such as one disclosed in JP-A-HEI 2-269382, is used as the reflector.

However, although the reflectance of the reflector can be increased to some extent by using such a white polyester film whitened by adding a pigment such as titanium oxide, the increase of the reflectance is limited to an insufficient level. Moreover, since the pigment such as titanium oxide absorbs a light having a specific wave length, the reflectance in a certain area of wave length decreases. Consequently, a sufficiently bright scope cannot be obtained by using such a white polyester film whitened by a pigment as a reflector. Therefore, a brighter scope is required, and a reflector having a high reflectance over a broad area of wave length is strongly required.

It would be desirable to provide a reflector for a surface light source which has a high reflectance over a broad area of wave length and can obtain a bright scope of a liquid crystal display or an electric decorative board when the surface light source is employed for the display or the board.

A reflector used in a surface light source according to the present invention comprises a white polyester film in which fine voids are formed and whose apparent specific gravity is in the range of 0.5 to 1.2. Namely, the white polyester film is used as a substrate of a reflector for a surface light source.

In the reflector according to the present invention, fine voids are formed in the polyester film so that the polyester film has an apparent specific gravity in the range of 0.5 to 1.2. The fine voids uniformly diffuse a light without absorbing a light having a specific wave length and sufficiently whiten the film. Therefore, the reflector can have a sufficiently high reflectance over a broad area of wave length. When the reflector having a high reflectance is used in a surface light source having a side light system, a bright scope easy to see can be obtained.

Some preferred exemplary embodiments of the invention will now be described with reference to the accompanying drawings which are given by way of example only, and thus are not intended to limit the present invention.

FIG. 1 is a graph showing the relationship between the wave length and the reflectance of a white polyester film used as a substrate for a reflector of a surface light source, according to an embodiment of the present invention.

FIG. 2 is a graph showing the relationships between the wave lengths and the reflectances of polyester films in examples and comparative examples.

FIG. 3 is a schematic sectional view of a surface light source having a side light system.

Next, the present invention will be explained in more detail by embodiments and examples. However, the present invention is not restricted by the embodiments and examples.

The white polyester film used as a substrate for the reflector according to the present invention must contain fine voids. The fine void means a void having a size of not greater than 100 μm . The shape of the void is not particularly restricted, and the shape may be a sphere, a flat shape or so forth. If an additive such as a pigment or a color is used to whiten a film and increase the reflectance of the film, the additive absorbs a light with a specific wave length and the reflectance in a certain area of wave length decreases. In the present invention, such an absorption of light can be suppressed to an extremely low level by whitening the polyester film and increasing the reflectance of the polyester film by fine voids.

The apparent specific gravity of the white polyester film according to the present invention must be in the range of 0.5 to 1.2. Since the white polyester film contains fine voids, the apparent specific gravity of the white polyester film decreases as compared with that of an ordinary polyester film. If the apparent specific gravity of the white polyester film is lower than 0.5, the amount of the fine voids is too much, and the film becomes too weak in strength as a substrate for the reflector. Further, a film breakage is liable to occur in the film formation process. If the apparent specific gravity of the white polyester film is higher than 1.2, the amount of the fine voids is too little, and a sufficiently high reflectance cannot be obtained and the film cannot be sufficiently whitened. Therefore, a sufficiently bright scope cannot be obtained when the film is used as a substrate for a reflector of a surface light source for a liquid crystal display etc.

The reflector according to the present invention comprises the white polyester film. Namely, the white polyester film is used as a substrate for the reflector. The thickness of a surface light source can be made sufficiently thin by using the white polyester film. Moreover, the white polyester film can be produced at a relatively low cost. Furthermore, since the polyester film has a high heat resistance, a high safety can be ensured even if the film is exposed to a light source having a relatively high temperature.

In the present invention, "polyester" means a polymer obtained by the condensation polymerisation of a diol and a dicarboxylic acid. As the dicarboxylic acid, terephthalic acid, isophthalic acid, phthalic acid, naphthalenedicarboxylic acid, adipic acid, sebacic acid can be used. As the diol, ethylene glycol, trimethylene glycol, tetramethylene glycol, cyclohexanedimethanol can be used. More concretely, for example, polytetramethylene terephthalate, polyethylene-p-oxybenzoate, poly-1,4-cyclohexanedimethylene terephthalate, polyethylene-2,6-naphthalenedicarboxylate can be used. Of course, these polyesters may be either homopolymer or copolymer. As a component to be copolymerized, diol component such as diethylene glycol, neopentyl glycol or polyalkylene glycol and dicarboxylic acid such as adipic acid, sebacic acid, phthalic acid, isophthalic acid or 2,6-naphthalenedicarboxylic acid can be used. In the present invention, particularly polyethylene terephthalate is preferable from the viewpoint of water resistance, chemical resistance and durability. To the polyester, various kinds of known additives, for example, an oxidation inhibitor, an antistatic agent, etc. may be added by a volume which does not decrease the advantages according to the present invention.

Since a white pigment has been added in order to whiten the above polyester film in the conventional method, increase of the reflectance of the film has been limited to a relatively low level because the particles of the pigment have a characteristic which absorbs a light having a specific wave length, and therefore, a sufficiently bright scope could not be obtained when such a film was used as a reflector. In the present invention, however, the polyester film is whitened by forming fine voids in the interior of the film and diffusing a light by the voids. By this, a high reflectance, which has not been obtained in the conventional films, can be achieved.

The fine voids are formed by finely dispersing a polymer incompatible with a matrix material of the film, for example, a polyester, and stretching the film uniaxially or biaxially. When the film is stretched, a void is formed around each particle of the incompatible polymer. Since the formed fine voids operate to diffuse a light, the film is whitened and a high reflectance can be obtained. The incompatible polymer means a polymer which does not dissolve into a polyester. As such an incompatible polymer, poly-3-methylbutene-1, poly-4-methylpentene-1, polypropylene, polyvinyl-t-butane, 1,4-transpoly-2,3-dimethylbutadiene, polyvinylcyclohexane, polystyrene, polyfluorostyrene, cellulose acetate, cellulose propionate or polychlorotrifluoroethylene can be used. Among these polymers, polyolefine, particularly polymethylpentene is preferable, because fine voids can be easily formed when the film is stretched, and further, since the polymer has a high transparency, absorption of a light by the film itself is very little and the light diffused by the voids substantially is not absorbed by the film. Therefore, when such a film is employed as a reflector of a surface light source, a scope having a high brightness can be obtained.

The content of the incompatible polymer is preferably in the range of 2 to 25 wt%. If the content is lower than the above range, a sufficient whitening cannot be achieved and a high reflectance cannot be obtained. If the content is higher than the above range, the strength of the film becomes too small.

The index of whiteness of the film thus obtained is preferably not less than 70%, and more preferably not less than 80%. Although a high brightness of a scope is required when the film is used as a reflector for

a surface light source, further it is also required to increase the whiteness of the scope. Therefore, the index of whiteness of the film is preferably as high as possible.

In the present invention, preferably a density lowering assistant is added to the film in order to uniformly disperse the incompatible polymer and form the fine voids sufficiently. Uniform fine voids can be formed by the uniform dispersion of the incompatible polymer, and degree of the whiteness, ultimately the reflectance can be uniform. The density lowering assistant is a specified compound which is added together with the incompatible polymer, disperses the incompatible polymer very finely, accelerates the generation of voids formed at boundary between the polyester and the incompatible polymer, and is effective to lower the specific gravity of the film. As a density lowering assistant for polyester, for example, polyalkylene glycol such as polyethylene glycol, methoxypolyethylene glycol, polytetramethylene glycol or polypropylene glycol, or derivative thereof, or copolymer thereof such as polyethylene terephthalate-polyethylene glycol or polybutylene terephthalate-polytetramethylene glycol, ethylene oxide/propylene oxide copolymer, sodium dodecylbenzenesulfonic acid, sodium alkylsulfonic acid, or glyceric monostearate can be used. In the present invention, polyalkylene glycol, particularly polyethylene glycol, polytetramethylene glycol or a copolymer of such a polyalkylene glycol and a polyester is preferable. The content thereof is preferably in the range of 0.1 to 5 wt%. If the content is too small, the effect due to the addition of the density lowering assistant becomes too small. If the content is too large, the property of the film itself is damaged. Although the density lowering assistant may be directly added at a required content or it may be added to a matrix polymer of the film to make a master polymer and thereafter the master polymer is blended at an appropriate content so that the content of the density lowering assistant in the film is controlled to a required value, preferably the density lowering assistant is added after copolymerization with polyester. Because the above-mentioned advantages due to the density lowering assistant become remarkable by adding it after copolymerization with polyester. In this case, the polyester copolymerized with the density lowering assistant may be different from the polyester used as a matrix of the film. Furthermore, the density lowering assistant may be mixed with polyester after the density lowering assistant has been added to and blended with the incompatible polymer. In such a case, since the density lowering assistant is added in advance to the incompatible polymer whose composition ratio in the film is relatively small, the density lowering assistant easily and efficiently acts the boundary between the polyester and the incompatible polymer, and a high effect can be obtained even if the amount of addition of the density lowering assistant is small.

In the present invention, the mean reflectance of the surface of the white polyester film in the range of wave length of a light of 400 to 700 nm is preferably not less than 90%, and further, the difference between the maximum and the minimum of the reflectance in the range of wave length is preferably not greater than 10%. This property is represented by, for example, a characteristic curve H1 shown by a continuous line in FIG. 1. Namely, the mean reflectance is not less than 90% in the main wave length area of 400 to 700 nm, and the difference between the maximum and the minimum of the reflectance in the main area is not greater than 10%. If the mean reflectance is lower than the above value, the scope tends to be yellow in the relatively low wave length area of the range and tends to be blue in the relatively high wave length area of the range when the white polyester film is used as a substrate for the reflector of a surface light source. However, the tendency to be yellow or blue can be prevented by the high mean reflectance of not less than 90%. Further, a uniform and bright scope can be obtained by suppressing the difference between the maximum and the minimum of the reflectance to a small value within 10%.

Moreover, the mean reflectance of the surface of the white polyester film in the range of wave length of a light of 330 to 380 nm is also preferably not less than 90%. This property is represented by, for example, a characteristic curve H2 shown by a dashed line in FIG. 1. It is possible to obtain a further bright scope by giving this property.

In the present invention, a glossiness G_1 under a condition of an angle of incidence of 60° and an angle of reflection of 60° is preferably not greater than 50%, more preferably not greater than 40%, and further more preferably not greater than 30%. A light introduced through an edge of a transparent light guiding plate is diffused by a halftone dot print and emitted toward a scope. A light leaked from the halftone dot print is reflected by a reflector. In the reflection, if the glossiness G_1 is greater than 50%, most of the reflection is a mirror reflection and the light turned by the surface of the reflector is reflected again by the surface of the transparent light guiding plate. Therefore, the light cannot be emitted toward the scope. If such a reflection between the surface of the reflector and the transparent light guiding plate is repeated, the light escapes from the edge of the light guiding plate or is absorbed by the light guiding plate. As a result, a bright scope cannot be obtained. In contrast, when the glossiness G_1 is not greater than 50%, most of the reflection at the surface of the reflector is a diffusing reflection, and most of the light can be emitted toward the scope efficiently and without being absorbed. As a result, a scope having a high brightness can be

obtained.

Further, when a glossiness under a condition of an angle of incidence of 60° and an angle of reflection of 45° is represented by G_2 and a glossiness under a condition of an angle of incidence of 60° and an angle of reflection of 75° is represented by G_3 , the white polyester film preferably satisfies the following equations.

$$G_2/G_1 \geq 0.05$$

$$G_3/G_1 \geq 0.05$$

More preferably the following equations are satisfied.

$$G_2/G_1 \geq 0.1$$

$$G_3/G_1 \geq 0.1$$

Further more preferably the following equations are satisfied.

$$G_2/G_1 \geq 0.2$$

$$G_3/G_1 \geq 0.2$$

As described above, as the diffusing reflection becomes intense, the scope is brighter. Namely, as the glossinesses G_2 and G_3 representing the intensity of the diffusing reflection become large relative to the glossiness G_1 representing the intensity of the mirror reflection, the scope is brighter. If G_2/G_1 is less than 0.05 or G_3/G_1 is less than 0.05, the diffusing reflection is insufficient and a sufficiently bright scope cannot be obtained even if G_1 is not greater than 50%.

In the present invention, the surface roughness of the white polyester film is preferably not less than 0.1 μm by center line average height R_a , and more preferably not less than 0.15 μm . The surface is preferably rough in order to design the surface having glossinesses such as those described above. If the surface roughness R_a is less than 0.1 μm , it is difficult to obtain the above glossinesses.

Further, the ratio of the maximum height R_t and the center line average height R_a of the surface roughness R_t/R_a is preferably not less than 5, and more preferably not less than 10. The diffusing reflection can be achieved more easily and a brighter scope can be obtained in a condition where the surface roughness is averagely at a low level and greatly rough portions exist in the surface than in a condition where the surface roughness is averagely at a high level.

In the present invention, the white polyester film may have a lamination structure of a plurality of layers. For example, lamination structures of two layer structure of A/B and three layer structure of A/B/A can be employed. In such cases, preferably the B-layer contains fine voids and the A-layer contains inorganic particles at a content of 5 to 25 wt%. More preferable content of the inorganic particles is in the range of 10 to 20 wt%. It is possible to achieve a high reflectance due to fine voids as well as to design a surface having desirable glossinesses by the lamination structure. Moreover, since the characteristic of the surface of the film can be maintained to be a characteristic of polyester itself, a good adhesive property of the surface (for example, ink adhesive property or lamination property) can be ensured. Furthermore, since a diffusion of light occurs at a boundary between the layers, a higher reflectance can be obtained. With respect to the content of inorganic particles, if the content is less than 5 wt%, a characteristic of the surface to be aimed cannot be easily obtained. If the content is greater than 25 wt%, the stretching ability of the film deteriorates.

As the material of the inorganic particles, silica and calcium carbonate are preferable. Particularly, calcium carbonate is preferable. The light absorbed by calcium carbonate particles is very little, and thereby a film substrate having a high reflectance can be provided. Further, since calcium carbonate itself has a function which forms voids, the reflectance can be further increased.

As the inorganic particles to be contained, a mixture of particles having a mean particle diameter of 0.5 to 2 μm and particles having a mean particle diameter of 2 to 10 μm is preferable. An appropriate surface roughness and an appropriate diffusion of light can be obtained by the particles having a mean particle diameter of 0.5 to 2 μm , and at the same time, a sufficient diffusion of light can be achieved by the particles having a mean particle diameter of 2 to 10 μm , thereby obtaining a desirable characteristic of the surface.

The process for adding the particles is not particularly restricted. The particles can be added in an extrusion process. Alternatively, the particles may be added by coating. Even if the addition of the particles is carried out by coating, a bright scope can be obtained similarly to that obtained by the addition in an

extrusion process.

In the white polyester film according to the present invention, a fluorescent whitening agent may be added. When the film has a lamination structure, a fluorescent whitening agent is preferably added to an outermost layer. By addition of the fluorescent whitening agent, a white polyester film having a mean reflectance of the surface in the range of wave length of a light of 330 to 380 nm of not less than 90% can be obtained. As a result, a brighter scope can be obtained. The process for adding the fluorescent whitening agent is not particularly restricted. The fluorescent whitening agent can be added in an extrusion process. Alternatively, the fluorescent whitening agent may be added by coating. Even if the fluorescent whitening agent is added by coating, a bright scope can be obtained similarly to that obtained by the addition in an extrusion process. As the fluorescent whitening agent, "OB-1" produced by Eastman Corporation, "Uvitex-OB" produced by Ciba-Geigy Corporation, "Uvitex-MD" produced by Ciba-Geigy Corporation or "JP-Conc" produced by Nihon Kagaku Kogyosho Corporation can be used.

Next, a process for producing the film according to the present invention will be explained. However, the process is not particularly restricted by the following one.

Polymethylpentene is blended as a incompatible polymer and polyethylene glycol is blended as a density lowering assistant, respectively, with polyethylene terephthalate. After sufficient blending and drying, the mixture is supplied to an extruder heated at a temperature of 270-300 °C. In a case where a single layer film is made by the polymer, two kinds of the inorganic particles having different mean particle diameters are added as aforementioned. In a case where a film having a lamination structure is made by the polymer, polyethylene terephthalate containing aforementioned two kinds of the inorganic particles having different mean particle diameters is supplied to an extruder "A", the above mixture is supplied to an extruder "B", and the two kinds of polymers are laminated in a lamination structure of A/B or A/B/A before entering into a T-type die or in a T-type laminating die.

The molten sheet delivered out from the die is cooled and solidified on a drum having a temperature of 10-60 °C while applying an electrostatic charge. The sheet is introduced into a group of rollers heated at a temperature of 80-120 °C, the sheet is stretched in the longitudinal direction at a draw ratio of 2-5 times during passage through the rollers, and thereafter, the uniaxially stretched film obtained is cooled by a group of rollers having a temperature of 20-50 °C. The film is introduced into a tenter while the edges of the film are clamped by clips. In the tenter, the film is stretched in the transverse direction in a heated atmosphere having a temperature of 90-140 °C. Although both the draw ratios in the longitudinal and transverse directions are in the range of 2 to 5 times, the area ratio between the non-stretched sheet and the biaxially stretched film is preferably in the range of 6 to 20 times. If the area ratio is less than 6 times, whitening of the film is insufficient. If the area ratio is greater than 20 times, a breakage of the film is liable to occur. After stretching, a thermosetting is conducted in the tenter at a temperature of 150-240 °C in order to give a flatness and a dimensional stability to the biaxially stretched film. Thereafter, the film is uniformly and gradually cooled to a room temperature, and wound.

The white polyester film thus obtained has a high reflectance of not less than 90% in the range of wave length of a light of 400 to 700 nm, and the dispersion of the reflectance in the range is very small. When the white polyester film is used as a substrate for a reflector of a surface light source having a side light system, a bright scope and a scope easy to see can be obtained. Further, since the white polyester film according to the present invention has an excellent mean reflectance in the specified range of wave length, the film can be utilized for various uses other than a reflector of a surface light source. For example, when the film is used as a receptor of a bar code printer, the contrast between the bar code portions and the film becomes clear, and accordingly the accuracy for reading can be increased. Further, in a usual printing, the film indicates a very clear and bright whiteness, and a clean and excellent finish can be obtained.

Next, methods for determining and estimating the characteristics in the present invention will be explained.

(1) Glossiness:

The glossiness is determined using a glossiness meter of type VG-107 produced by Nippon Densyoku Kogyo Corporation, under a condition of an angle of incidence and an angle of reflection defined in JIS Z-8741.

(2) Mean reflectance:

An integrating sphere is attached to a spectrophotometer (UV-260: produced by Shimadzu Seisakusyo Corporation), a reflectance is determined in the ranges of wave length of 400 to 700 nm and 330 to 380 nm

when the reflectance of a MgO plate is defined as 100%. The reflectances are read from the chart obtained at an interval of 5 nm, and the average value is defined as the mean reflectance.

(3) Difference between the maximum and the minimum of the reflectance in the range of wave length of 400 to 700 nm:

The reflectance is determined in the range of wave length of 400 to 700 nm in the manner defined in the above item (2). The maximum value and the minimum value of the reflectance are read from the chart obtained, and the difference between the maximum and the minimum is calculated.

(4) Apparent specific gravity:

The film is cut at 100 mm × 100 mm. The thickness of the film sample is determined at points of not less than 10 points, using a dial gauge (No. 2109-10: produced by Mitsutoyo Seisakusyo Corporation) attached with a probe (No. 7002) having a diameter of 10 mm, and the average value "d" μm of the thicknesses determined is calculated.

The weight of the film sample is determined by a direct reading balance and the weight "w" g is read by a unit of 10⁻⁴ g.

The apparent specific gravity is defined by the following equation.

$$\text{apparent specific gravity} = w/d \times 100$$

(5) Brightness of scope:

In the device shown in FIG. 3, a halftone dot printing is performed on an acrylic plate having a thickness of 3 mm, a film is set as reflector 11, and a light is applied from an edge by a fluorescent tube of 6 watts. The brightness of scope 12 is determined at 15 points by a brightness meter (LS-110: produced by Minolta Corporation), and the average value is defined as the brightness of the scope.

(6) Color tone of scope:

The color tone of a scope is determined by observation. A scope which indicates white is defined as "white", a scope which tends to be yellow is defined as "yellow", and a scope which tends to be blue is defined as "blue".

(7) Surface roughness Ra, Rt:

The surface roughness is determined by a stylus type surface roughness tester (ET-10: produced by Kosaka Kenkyusyo Corporation) based on JIS B-0601 which corresponds to ISO-R-468 or DIN-4768.

(8) Mean particle diameter of inorganic particles:

The inorganic particles are dispersed in ethanol, the particle size distribution is determined by a decanter type particle size distribution measuring apparatus (CAPA500: produced by Horiba Seisakusyo Corporation), and the mean particle diameter is calculated from the determined particle size distribution.

EXAMPLES

Preferred examples will be hereinafter explained together with some comparative examples. The resulted data of determination and estimation are shown in Tables 1 and 2 and FIG. 2.

Example 1

Pellets of polyethylene terephthalate, and master pellets prepared by adding polyethylene glycol having a mean molecular weight of 4000 to polyethylene terephthalate when the polyethylene terephthalate was polymerized, were vacuum dried at a temperature of 180 °C for three hours, and thereafter, the respective

pellets were blended so that the content of polyethylene terephthalate was 89 wt%, the content of polyethylene glycol was 1 wt% and the content of polymethylpentene was 10 wt%. The mixture was supplied to an extruder heated at a temperature of 270 to 300 °C, the mixture was melt-extruded, and the molten polymer was delivered out from a T-type die in a form of a sheet. The sheet was cooled and solidified by a cooling drum whose surface temperature was controlled at 25 °C. The sheet was introduced into a group of rollers heated at a temperature of 85 to 98 °C, the sheet was stretched in the longitudinal direction at a draw ratio of 3.4 times and thereafter the uniaxially stretched film was cooled by a group of rollers controlled at 25 °C. The film was introduced into a tenter while the edges of the film were cramped by running clips, and the film was stretched in the transverse direction at a draw ratio of 3.6 times in the atmosphere having a temperature of 130 °C in the tenter. After that, the film was thermoset in the tenter at a temperature of 230 °C, the film was uniformly and gradually cooled to a room temperature, and thereafter, the film was wound. The thickness of the film obtained was 188 μm. The characteristics of the film obtained are shown in Tables 1 and 2 and FIG. 2. As shown in Tables 1 and 2, the white polyester film obtained has a high brightness of scope when it is used as a substrate for a reflector of a surface light source.

Example 2

In Example 1, master pellets of a fluorescent whitening agent (OB-1: produced by Eastman Corporation) were added such that the content of the fluorescent whitening agent was 0.03 wt%. A film having a thickness of 188 μm was made in a manner similar to that in Example 1. The characteristics of the film obtained are shown in Tables 1 and 2 and FIG. 2. A scope brighter than that in Example 1 was achieved.

Example 3

Pellets of polyethylene terephthalate, and master pellets prepared by adding polyethylene glycol having a mean molecular weight of 4000 to polyethylene terephthalate when the polyethylene terephthalate was polymerized, were vacuum dried at a temperature of 180 °C for three hours, and thereafter, the respective pellets were blended so that the content of polyethylene terephthalate was 89 wt%, the content of polyethylene glycol was 1 wt% and the content of polymethylpentene was 10 wt%. The mixture was supplied to an extruder "B" heated at a temperature of 270 to 300 °C. Pellets of polyethylene terephthalate containing calcium carbonate particles having a mean particle diameter of 1.1 μm at a content of 14 wt% were supplied to an extruder "A" after the pellets were dried in the same manner. The polymers extruded by the extruders "A" and "B" were laminated to form a three layer lamination structure of A/B/A, and the laminated polymers were delivered out from a T-type die in a form of a sheet. The sheet was stretched in the same manner as that in Example 1 and a biaxially stretched film having a thickness of 188 μm was obtained. The thickness ratio of three layers of the film obtained was 12/164/12 μm. The characteristics of the film obtained are shown in Tables 1 and 2 and FIG. 2. A scope having a high brightness could be achieved.

Example 4

In Example 3, master pellets of a fluorescent whitening agent (OB-1: produced by Eastman Corporation) were added to the raw material to be supplied to the extruder "A" such that the content of the fluorescent whitening agent was 0.03 wt%. A film having a thickness of 188 μm was made in a manner similar to that in Example 3. The characteristics of the film obtained are shown in Tables 1 and 2 and FIG. 2. The reflectance of the film was increased by addition of the fluorescent whitening agent, and a scope brighter than that in Example 3 was obtained.

Example 5

A film was made in the same manner as that in Example 3, and a corona treatment was applied to the film. A coating solution of a mixture of acrylic resin (Coatex: produced by Toray Industries, Inc.)/silica particles (diameter: 1 μm) /isocyanate/fluorescent whitening agent (OB-1: produced by Eastman Corporation) whose ratio was 100/5/20/1 was prepared by diluting the mixture with toluene/methylethylketone (= 1/1) so that the content of the mixture was 20 wt%. The solution thus prepared was coated onto the film by a gravure coater to form a coating layer having a thickness of 3 μm.

The characteristics of the film obtained are shown in Tables 1 and 2 and FIG. 2. A scope having a high

brightness could be achieved even by coating the fluorescent whitening agent, similarly to in Example 4.

Comparative Example 1

5 Pellets of polyethylene terephthalate, and master pellets prepared by compounding titanium dioxide particles with polyethylene terephthalate, were vacuum dried at a temperature of 180°C for three hours, and thereafter, the respective pellets were blended so that the content of titanium dioxide particles was 14 wt%. The mixture was supplied to an extruder and extruded molten polymer was delivered out from a T-type die in a form of a sheet. Thereafter, a film having a thickness of 188 μm was made in a manner similar
10 to that in Example 1. The characteristics of the film obtained are shown in Tables 1 and 2 and FIG. 2. The brightness of scope was decreased because of the absorption of light due to titanium dioxide particles.

Comparative Example 2

15 A white synthetic paper having a thickness of 200 μm ("YUPO" FPG200: produced by Ouji Yuka Synthetic Paper Corporation) was used as a reflector. The characteristics of the paper are shown in Tables 1 and 2. A high brightness of scope could not be obtained by the synthetic paper.

Example 6

20 In Example 3, pellets of polyethylene terephthalate containing calcium carbonate particles having a mean particle diameter of 1.1 μm at a content of 14 wt% and silica particles having a mean particle diameter of 4 μm at a content of 3 wt% were supplied to an extruder "A". A film having a thickness of 188 μm was made in a manner similar to that in Example 3. The characteristics of the film obtained are shown
25 in Tables 1 and 2. A scope brighter than that in Example 3 was obtained by roughening the surface of the film more than in Example 3, decreasing the glossiness and increasing the diffusing reflection.

Example 7

30 A film was made in the same manner as that in Example 3, and a corona treatment was applied to the film. A coating solution of a mixture of acrylic resin (Coatex: produced by Toray Industries, Inc.)/silica particles (diameter: 1 μm)/silica particles (diameter: 4 μm)/isocyanate/fluorescent whitening agent (OB-1: produced by Eastman Corporation) whose ratio was 100/5/3/20/1 was prepared by diluting the mixture with toluene/methylethylketone (= 1/1) so that the content of the mixture was 20 wt%. The solution thus prepared
35 was coated onto the film by a gravure coater to form a coating layer having a thickness of 3 μm .

The characteristics of the film obtained are shown in Tables 1 and 2. A scope having a high brightness similar to that in Example 6 could be obtained by coating the two kinds of inorganic particles having different diameters.

Example 8

40 In Example 3, dried pellets of polyethylene terephthalate was supplied to an extruder "A" and a film having a thickness of 188 μm was made in a manner similar to that in Example 3. The characteristics of the film obtained are shown in Tables 1 and 2. Although a certain high brightness of scope could be obtained, a
45 higher brightness of scope such as one in Example 3 could not be obtained because the glossiness was high and the diffusing reflection was poor.

Example 9

50 A film having a thickness of 188 μm was made in the same manner as that in Example 8, and a corona treatment was applied to the film. Next, the coating was performed in the same manner as that in Example 7, and a coating layer having a thickness of 3 μm was formed. The characteristics of the film obtained are shown in Tables 1 and 2. Although a high brightness of scope such as one in Example 8 could not be obtained by the film itself, a sufficiently high brightness of scope could be obtained by such a coating and
55 increasing the diffusing reflection.

Example 10

In Example 1, master pellets prepared by copolymerizing polytetramethylene glycol with polyethylene terephthalate instead of polyethylene glycol was used, and a film having a thickness of 188 μm was made in a manner similar to that in Example 1. The characteristics of the film obtained are shown in Tables 1 and 2. The reflectance was increased as compared with that of Example 1, and a brighter scope could be obtained.

TABLE 1

	Apparent specific gravity	Glossiness					Mean reflectance 400-700 nm (%)	Difference between maximum and minimum of reflectance (%)
		G1 (%)	G2 (%)	G3 (%)	G2/G1	G3/G1		
Example 1	0.80	41	5	5	0.12	0.12	93	5
Example 2	0.80	41	5	5	0.12	0.12	94	5
Example 3	0.80	28	6	5	0.21	0.18	96	4
Example 4	0.80	28	6	5	0.21	0.18	97	4
Example 5	0.80	32	6	5	0.19	0.16	97	4
Comparative Example 1	1.50	58	4	4	0.07	0.07	85	12
Comparative Example 2	0.79	15	8	7	0.53	0.47	90	10
Example 6	0.80	16	8	6	0.49	0.38	96	4
Example 7	0.80	20	8	5	0.40	0.25	96	4
Example 8	0.83	110	4	3	0.04	0.03	94	6
Example 9	0.83	23	8	5	0.35	0.22	95	5
Example 10	0.80	40	5	5	0.13	0.13	95	4

TABLE 2

	Mean reflectance 330-380 nm	Surface roughness			Brightness of scope	Color tone of scope
		Ra	Rt	Rt/Ra		
	(%)	(μm)	(μm)	(μm)	(nit)	
Example 1	88	0.11	1.0	9	198	white
Example 2	100	0.11	1.0	9	203	white
Example 3	92	0.17	1.9	11	201	white
Example 4	102	0.18	1.8	10	205	white
Example 5	102	0.15	1.7	11	204	white
Comparative Example 1	25	0.10	0.7	7	180	yellow
Comparative Example 2	57	0.55	6.1	11	182	yellow
Example 6	94	0.40	4.3	11	205	white
Example 7	100	0.33	4.0	12	206	white
Example 8	88	0.03	0.3	10	194	yellow
Example 9	99	0.33	3.4	10	202	white
Example 10	90	0.12	1.1	9	202	white

Claims

1. A reflector (11) used in a surface light source characterized in that said reflector (11) comprises a white polyester film in which fine voids are formed and whose apparent specific gravity is in the range of 0.5 to 1.2.
2. The reflector (11) according to claim 1, wherein the mean reflectance of the surface of said white polyester film in the range of wave length of a light of 400 to 700 nm is not less than 90%, and the difference between the maximum and the minimum of the reflectance in said range of wave length is not greater than 10%.

3. The reflecter (11) according to claim 1 or 2, wherein, when a glossiness under a condition of an angle of incidence of 60° and an angle of reflection of 60° is represented by G_1 , a glossiness under a condition of an angle of incidence of 60° and an angle of reflection of 45° is represented by G_2 and a glossiness under a condition of an angle of incidence of 60° and an angle of reflection of 75° is represented by G_3 , said white polyester film satisfies the following equations:

$$\begin{aligned} G_1 &\leq 50\%, \\ G_2/G_1 &\geq 0.05 \text{ and} \\ G_3/G_1 &\geq 0.05. \end{aligned}$$

4. The reflecter (11) according to any preceding claim, wherein the surface roughness of said white polyester film is not less than 0.1 μm by center line average height R_a , and the ratio of the maximum height R_t and the center line average height R_a of the surface roughness R_t/R_a is not less than 5.

5. The reflecter (11) according to any preceding claim, wherein said white polyester film contains a polyolefine at a content of 2 to 25 wt%, and the polyester film is biaxially stretched.

6. The reflecter (11) according to claim 5, wherein said polyolefine is polymethylpentene.

7. The reflecter (11) according to any preceding claim, wherein said white polyester film contains a density lowering assistant.

8. The reflecter (11) according to claim 7, wherein said density lowering assistant is polyalkylene glycol, a derivative thereof or a copolymer including polyalkylene glycol or a derivative of polyalkylene glycol.

9. The reflecter (11) according to any preceding claim, wherein said white polyester film has a lamination structure of a plurality of layers.

10. The reflecter (11) according to claim 9, wherein said white polyester film has a lamination structure of two layer structure of A/B, the B-layer contains fine voids and the A-layer contains inorganic particles at a content of 5 to 25 wt%.

11. The reflecter (11) according to claim 9, wherein said white polyester film has a lamination structure of three layer structure of A/B/A, the B-layer contains fine voids and the A-layer contains inorganic particles at a content of 5 to 25 wt%.

12. The reflecter (11) according to claim 10 or 11, wherein said inorganic particles are calcium carbonate particles.

13. The reflecter (11) according to claim 10 or 11, wherein said inorganic particles are a mixture of particles having a mean particle diameter of 0.5 to 2 μm and particles having a mean particle diameter of 2 to 10 μm .

14. The reflecter (11) according to any preceding claim, wherein the mean reflectance of the surface of said white polyester film in the range of wave length of a light of 330 to 380 nm is not less than 90%.

15. The reflecter (11) according to claim 14, wherein said white polyester film has a lamination structure of a plurality of layers, and at least an outermost layer of the plurality of layers contains a fluorescent whitening agent.

16. The reflecter (11) according to claim 14, wherein a coating layer is provided on said white polyester film, and the coating layer contains a fluorescent whitening agent.

17. A white polyester film in which fine voids are formed and whose apparent specific gravity is in the range of 0.5 to 1.2, characterized in that the mean reflectance of the surface of said white polyester film in the range of wave length of a light of 400 to 700 nm is not less than 90% and the difference between the maximum and the minimum of the reflectance in said range of wave length is not greater than 10%.

FIG. 1




FIG. 2




FIG. 3




FIG. 1




FIG. 2





FIG. 3



(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets




(11) Publication number:

0 496 323 A3

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **92100847.0**(51) Int. Cl.⁵: **G02B 1/04, G02F 1/13,
G09F 9/00**(22) Date of filing: **20.01.92**(30) Priority: **22.01.91 JP 20328/91**
27.03.91 JP 63517/91(43) Date of publication of application:
29.07.92 Bulletin 92/31(84) Designated Contracting States:
BE DE FR GB IT LU NL(88) Date of deferred publication of the search report:
10.02.93 Bulletin 93/06(71) Applicant: **TORAY INDUSTRIES, INC.**
2-1, Nihonbashi Muromachi 2-chome
Chuo-ku
Tokyo 103(JP)(72) Inventor: **Miyakawa, Katsutoshi**
16, Takehana Jizoji, Minami-machi,
Yamashina-ku
Kyoto-shi, Kyoto 607(JP)
Inventor: **Tsunashima, Kenji**
1-22, Daigo Kamihayama-cho, Fushimi-ku
Kyoto-shi, Kyoto 601-13(JP)
Inventor: **Aoki, Seizo**
454, Oono, Tsuchiyama
Koka-gun, Shiga, 528-02(JP)(74) Representative: **Kador & Partner**
Corneliusstrasse 15
W-8000 München 5(DE)(54) **Reflector for a surface light source.**

(57) A reflector (11) used in a surface light source comprising a white polyester film in which fine voids are formed and whose apparent specific gravity is in the range of 0.5 to 1.2. The reflectance of the polyester film can be increased by the fine voids. When the reflector having a high reflectance is used in a surface light source having a side light system, a bright scope easy to see can be obtained.

FIG. 1**EP 0 496 323 A3**



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 92 10 0847

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
A	US-A-4 770 931 (MARK A. POLLOCK) * claim 1 * * column 2, line 45 - line 62 * * column 5, line 18 - line 19 * ---	1,17	G02B1/04 G02F1/13 G09F9/00
P,A	US-A-4 994 312 (LARRY K. MAIER) * figure 1 * * column 2, line 45 - line 62 * * column 5, line 18 - line 19 * ---	1,17	
A	US-A-4 187 113 (CARL F. MATHEWS) * claim 1 * ---	1,17	
A	GB-A-2 215 268 (MOBIL PLASTICS EUROPE) * claim 1 * * page 3, paragraph 2 * ---	17	
A	EP-A-0 167 721 (MITSUBISHI RAYON CO. LTD.) * claim 1 * -----	1	
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			G02B G02F G09F F21V C08J
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 14 DECEMBER 1992	Examiner DEPIJPER R.D.C.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- * : member of the same patent family, corresponding document	

EPO FORM 1503 (12.92) (P0607)